

PRODUCT DESCRIPTION

FT-9500-QF is a fast-setting, two-component modified urethane. Its extremely low viscosity allows for deep penetration into concrete as a primer or thoroughly wetting out selected aggregate to form a high-strength concrete repair.

USES

- Rapid setting concrete primer
- Rapid setting, high strength concrete patching and repair material

ADVANTAGES

- Excellent abrasion resistance
- High impact resistance
- Low odor
- Meets SCAQMD requirements
- Minimal prep/down time
- Quick set time
- USGBC LEED, EQ Credit 4.3: Low-emitting VOC Compliant Materials

COLOR

Amber or Medium Gray

Note: Due to its chemical composition, FT-9500-QF will discolor when exposed to UV radiation.

TYPICAL PHYSICAL PROPERTIES

Property	Test Method	Value
Mix Ratio by Volume	NA	1:1
Pot Life @ 68°F	ISO 9514	5 minutes
Tack Free Time @ 68°F	ASTM D1640	10 minutes
Recoat Window	Internal	6 hours
VOC	ASTM D6511	5.5 g/L
Adhesion to Concrete	ASTM D7234	>150 psi
Compressive Strength (with sand)	ASTM C579	>4,250 psi

The values stated in this Product Data Sheet are based on system processing under controlled laboratory conditions. Equipment configuration and/or field application conditions may produce variances in the installed product values

SURFACE PREPARATION

Provide clean, dry, and sound concrete substrate. Concrete shall be allowed to cure for a minimum of 28 days.

Prepare concrete surfaces in accordance with SSPC-SP13/NACE No. 6 and achieve a Concrete Surface Profile of at least 3, measured using ICRI CSP Chips.

After surface preparation and prior to the application of Freedom Chemical Corporation products, test surface tensile strength of prepared concrete surfaces in accordance with ASTM D7234 and/or ASTM C1583. Minimum surface tensile strength shall be 300 psi. Refer to SSPC-SP13/NACE No. 6, Section 6, Table 2 for additional information.

Grinding is only permitted in areas that are inaccessible to standard abrasive blast equipment.

COVERAGE RATES

Material coverage rates shall be in accordance with project specification requirements or Freedom Chemical Corporation's Installation Procedure document(s), whichever is more stringent.

PACKAGING

10-gallon kit:

- Part A: 5 gallons liquid
- Part B: 5 gallons liquid **2-gallon kit:**
- Part A: 1 gallons liquid
- Part B: 1 gallons liquid

MIXING & APPLICATION

Refer to appropriate Installation Procedure document(s) for detailed instructions.

CLEAN UP

User is responsible for reading, understanding, and following all recommendations on SDS. Dispose of all packaging and containers in accordance with local, state, and federal laws and regulations. Excess liquid materials should be mixed and allowed to cure. Once cured, dispose of cured material in accordance with local, state, and federal laws and regulations.

LIMITATIONS

Care shall be taken when applying Freedom Chemical Corporation products over substrates containing trapped moisture and/or where moisture vapor drive is present (i.e., metal pan decks, split slab membranes, etc.). Refer to Installation Procedure document(s) for substrate treatment prior to placement of any coatings.

Excess moisture vapor in concrete slabs may cause polyurea coating to delaminate, discolor, and/or cure improperly.

SHELF LIFE & STORAGE

Shelf life is one (1) year from the date of manufacture in original, unopened, factory-sealed containers under specified storage conditions.

Shipping and storage temperatures is 65°F to 90°F at (or below) 50% Relative Humidity. Avoid freezing temperatures. Do not store containers directly on ground. Always store on pallets or otherwise elevated.

Do not open containers until ready to use. Partially filled containers should be purged of air using nitrogen blanketing and sealed tightly when not in use.